
SMARTMolding UPDATE

D. Heider

Report Documentation Page				Form Approved OMB No. 0704-0188	
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE 26 AUG 2004		2. REPORT TYPE N/A		3. DATES COVERED -	
4. TITLE AND SUBTITLE SMARTMolding Update				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) University of Delaware Center for Composite Materials Newark, DE 19716				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release, distribution unlimited					
13. SUPPLEMENTARY NOTES See also ADM001700, Advanced Materials Intelligent Processing Center: Phase IV., The original document contains color images.					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT UU	18. NUMBER OF PAGES 21	19a. NAME OF RESPONSIBLE PERSON
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified			

Outline



- **Review of new VARTM process variations**
 - ◆ **Channel-Assisted Resin Transfer Molding (CARTM)**
 - ◆ **Interlaminar Flow Media**
 - ✧ Verdant Polybeam™
- **New Features of SMARTMolding Software Suite**
 - ◆ **Design Tool**
 - ✧ Incorporated commercially available Distribution Media into Database
 - ◆ **Intelligent Process Control System**
 - ✧ Added Intranet connectivity
 - ✧ Automated Vacuum Debulking
 - ✧ On-line Work Instructions
 - ✧ Virtual Checklist of all Processing Steps
 - ✧ Sensor Test
 - ◆ **New Data Review Graphical User Interface**
 - ✧ Allows on-line reporting on all recorded data over Intranet
 - ✧ Export to Excel, Printing Capability

Outline




- **New Features of SMARTMolding Software Suite**
 - ◆ **Recipe Definition GUI (In Progress)**
 - ✧ Complete Process Flow Description (Recipe) is automated
 - ✧ Checks on Database and Process Consistency
 - ◆ **Automated Statistical Analysis Tool (In Progress)**
 - ✧ Detects Outliers
 - ✧ Ranking of Important Process Variables
- **New Features of SMARTMolding Hardware Suite**
 - ◆ **Wireless Tool-Mounted Sensors (In Progress)**
 - ◆ **Tool-Mounted Time-Domain Reflectometry**
- **Technology Transfer**
 - ◆ **Important Conference Participation**
 - ✧ SMARTMolding Demonstration at SAMPE '03 Long Beach, CA
 - ✧ Invited Lecture "Intelligent Process Control For Automated VARTM Processing" Composite Fabricator Association (CFA) Liquid Molding Conference in Dayton, OH
 - ◆ **In Progress of Updating Beta-Sites with new Software Components**
 - ✧ NSWC Caderock has been updated
 - ◆ **Strong Interest in SMARTMolding from several Companies**
 - ✧ Boating
 - ✧ Wind Energy

The CARTM Process I



- **Channel-Assisted Resin Transfer Molding Process**
- **Patented and Commercially Licensed**
- **Similar attributes compared to FASTRAC, but flow media and completed double bagging systems are commercially available**



The CARTM Process II




- **System can be modeled as a typical VARTM process with distribution media**
 - ✦ **Permeability is a function of CARTM media (channel pattern) and differential vacuum pressure**
 - ✦ **Opportunity to optimize surface flow for complex structures by designing the CARTM layer (off-line control)**
 - ✦ **On-line flow control possible by adjusting differential vacuum pressure**
 - ✦ Zones
 - ✦ Vacuum gradient
 - ✦ Delay Lines

- **Establishment of a CARTM workcell at UD-CCM in July with help of “Why not Composites”**

Interlaminar Flow Medium



- Resin introduced through the preform via an integrated inter-laminar distribution media
- Peel ply not necessary
- Thick preforms can be divided in multiple laminates





Courtesy of

Polybeam Flow Media™



- Patented Polybeam technology increases permeability during infusion due to spring-back and reduces porosity after infusion due to unique compaction behavior




- Talks initiated with Verdant to evaluate compaction behavior and mechanical performance
 - ◆ Bonding to cored structure
 - ◆ Inter--laminar shear


SMARTMolding Software Suite



Design Tool




IPC System



Data Review



Statistical Package



Recipe GUI

Recipe ID	Recipe Name	Material	Temp	Pressure	Flow	Time
1	Example 1	20" by 24" E-Glass with V-30	120	10	1.0	1.0
2	Example 2	20" by 24" E-Glass with V-30	120	10	1.0	1.0
3	Example 3	20" by 24" E-Glass with V-30	120	10	1.0	1.0
4	Example 4	20" by 24" E-Glass with V-30	120	10	1.0	1.0
5	Example 5	20" by 24" E-Glass with V-30	120	10	1.0	1.0
6	Example 6	20" by 24" E-Glass with V-30	120	10	1.0	1.0
7	Example 7	20" by 24" E-Glass with V-30	120	10	1.0	1.0
8	Example 8	20" by 24" E-Glass with V-30	120	10	1.0	1.0
9	Example 9	20" by 24" E-Glass with V-30	120	10	1.0	1.0
10	Example 10	20" by 24" E-Glass with V-30	120	10	1.0	1.0


- Simple Interface, Limited to simple geometries
- Predicts Flow Times, Lead Length
- Optimizes # of Seq. Injection Lines
- Database with Material Properties

- Automates the VARTM Process
- Records the processing steps
- Reporting of collected data
- Enables statistical analysis
- Guidance Software to define process recipe

Added Permeability Data to Database of Commercially Available Distribution Media



Data Courtesy of
Gaetan Denis



- Database includes now 5 Distribution Media (4 more in progress)
- Design tool chooses DM based on lead length and flow times

Recipe Definition GUI



➤ Supports Definition of

◆ Process Set Points

- ◆ Vacuum Leak Level
- ◆ Resin Volume
- ◆ Debulking
 - ◆ Cycles
 - ◆ Vacuum Level and Cycle Time
- ◆ Infusion Setup
 - ◆ Sensors
 - ◆ Valves
 - ◆ Sequential Injection Script
- ◆ Dwell Time and Dwell Vacuum level

◆ Material Selection

- ◆ Materials and Material Sequence during Lay-up
- ◆ Resin
- ◆ Bagging
- ◆ Mold

➤ Validates complete definition of recipe

➤ Review Recipe Definition

The screenshot displays the SMARTMolding Recipes interface. The top window shows a list of recipes with columns for ID, Panel Part No, Panel Name, Mold, Layers, Bag, Dwell, Cure, and Infusion. Recipe 12 is selected. Below this, a 'New Recipe' dialog box is open, showing details for 'Example 10' (24" by 24" E-Glass with SC15). The dialog includes fields for Mold Class ID, Layers, Bag Class ID, Dwell ID, Cure ID, and Infusion ID. At the bottom, another table shows the current database of recipes.

ID	Panel Part No	Panel Name	Mold	Layers	Bag	Dwell	Cure	Infusion
9	Example 05	24" by 24" E-Glass with SC79	2	2	2	2	1	6
10	Example 06	24" by 24" E-Glass with SC79/SC15 Blend	2	2	2	2	1	7
11	Example 07	24" by 24" E-Glass with ResinInfusion 8605	2	2	2	3	1	8
12	Example 08	24" by 24" E-Glass with Newport NBV850	2	2	2	3	1	9
13	Example 09	24" by 24" E-Glass with VE100	2	2	2	1	1	10
14	Example 10	24" by 24" E-Glass with SC15	2	2	2	4	1	11
16	Example 11	24" by 24" S2-Glass with SC79	2	4	2	2	1	16
18	Example 12	24" by 24" S2-Glass with SC15	2	4	2	4	1	17
19	Example 13	24" by 24" S2-Glass with SC15+SC79 (1+1)	2	4	2	3	1	18
20	Example 14	24" by 24" S2-Glass with SC15+SC79 (1+1)B	2	4	2	2	1	18

New IPC Graphical User Interface Features 1/2




Intranet connectivity



IPC 1



IPC 2




Server



- Automatic Backups
- Multiple IPC's can be connected

On-Line Work Instructions



- MSDS
- Pictures
- AutoCAD drawings
- Video


Virtual Checklist of all Processing Steps



New IPC Graphical User Interface Features 2/2




Automated Vacuum Debulking



- Automatic Debulking
- Improves repeatability and reduces preform thickness prior to infusion

Sensor Test GUI




- Ensures sensor functionality
- Adjust resin arrival threshold for different resin systems

Data Review Graphical User Interface



DEMONSTRATION



Repeatability Analyses of the VARTM Process



- PhD student is establishing theoretical and experimental understanding of VARTM repeatability → see presentation of Amorous
- Boeing Corporation is supporting the VARTM repeatability project
 - ◆ Information will be provided from the AST Wing and CAI program
 - ◆ POC Boeing: Scott Holmes
V-22 Affordability
Integrated Defense Systems, PHL

Statistical Analysis Package



Objective

- ◆ Flag outliers based on process parameter values and reduce number of post-inspections
- ◆ Rank parameters based on their repeatability
- ◆ Identify parameters that relate to quality of part
- ◆ Detect quality based on parameter values

Approach

- ◆ Iterative statistical detection scheme for outliers
- ◆ Repeatability measure to rank parameters,

Data Analysis: Fiber Weight



Lognormal Distribution fits the Fiber Weight Data

➤ Discrete vs. Continuous

- ◆ Discrete parameters have one value per part, Ex. Fiber Weight
- ◆ Continuous parameters are time-dependent, Ex. Resin Weight Infused vs. Time


➤ Lognormal Distribution

- ◆ Assuming Lognormal distribution for process parameters (When RV X is lognormally distributed, then $\ln(X)$ is normally distributed.)



➤ Lognormal Validation

➤ Outlier Detection based on Probability Level

Normal Scores vs. Sorted Data Values for Fiber Weight



Additional Layer was added to part 03-00062 and 03-00063 creating two outlier.



Wireless Sensor Network




Objective:

- Reduce noise due to wiring
- Allow seamless switching of molds without connecting/disconnecting sensor cables

Approach:


- Using existing wireless sensor network technology
- Develop custom DAQ to connect locally to transmitter
 - ◆ DC-based flow measurement
 - ◆ Other sensors such as temperature and humidity sensor
- Wireless sensor network technology replaces multiplexing technology
- Sensor signal quality is improved due to a reduction in cross-talking and cable noise
- Simple plug & play reduces the setup time. System can be reduced if mold is scrapped



Improved Signal to Noise Ratio 5:1




Existing SMARTMolding System




$$\text{SNR}=10*\log(0.3/0.01)=4.7\text{db}$$

Wireless Single Sensor



$$\text{SNR}=10*\log(2.02/0.01)=23.05\text{ db}$$




Demonstration!!!

Tool-Embedded TDR Sensing




Technology benefits:

- ✓ Non-contact sensing;
- ✓ Sensing through release agent and gel coat;
- ✓ No post service required;
- ✓ Low cost manufacturing;
- ✓ Application for non-conductive polymer based tools with various curvatures.




5m Tall Structure Infusion



- ✓ Tool embedded TDR sensing has been tested during vertical infusion;
- ✓ TDR sensor response fits infused resin weight data very well.

✓ 1D TDR Flow data shows flow progression after fill factor shows no response

✓ The resin cures in bucket faster and stops injection in the preform



Summary



- New VARTM processes create opportunity for on-line control
- Additions to IPC software creates new capabilities (debulking) and adds to industrial requirements (work instructions, intranet capable)
- Major advances have been implemented to create user-friendly SMARTMolding environment
 - ◆ Recipe Definition
 - ◆ Data Review
- Data mining software components have been implemented to review automatically large amount of data collected and to detect processing outliers
- New sensor hardware shows promise for industrial environment
 - ◆ Reduced wire count
 - ◆ Tool-Mounted TDR allows monitoring through gel coat